

产品类别 Product Category	牌号Grade	测试标准、测试项目 Test criteria, test items							特性及用途 Property and Application
		熔指 MFI g/10min(230℃, 2.16kg)	密度 Density g/cm³	拉伸强度 Tensile Strengt h MPa	弯曲模 量 Flexura l modulu s Mpa	悬臂梁缺口 冲击强度 Notched Izod impact strength J/m	阻燃性 Flame retardance	灼热丝 GWIT℃	
		ASTM D1238	ASTM D792	ASTM D638	ASTM D790	ASTM D256	UL 94	IEC60695	
有卤阻燃 PP Halogen flame retardant PP	HRPP-F5V	5	1.36	24	2500	30	2.0mm 5VA	2.0mm 750	5VA, 干衣机底台、电控盒 5VA, dryer base, electronic control box
	FR-2015	8	1.33	20	2000	50	1.5mm V0 2.0mm 5VA	2.0mm 775	高GWIT, 空调外机阀罩、 把手 High GWIT, air conditioning external unit valve cover, handle
	HRPP-FV0	5	1.3	25	2300	35	1.5mm V0	2.0mm 725	耐热耐水, 洗衣机组件 Heat and water resistant, washing machine components
	FR-2017	6	1.25	26	2000	30	3.0mm V0	2.0mm 725	V0阻燃要求的制件 V0 flame retardant required parts
	FR-2018	10	1.01	30	1300	40	1.0mm V0	2.0mm 725	高光泽, 低密度, 抗菌卫浴: High gloss, low density, antibacterial bathroom accessory
V2阻燃PP V2 level flame retardant PP	FR-2030	20	1.0	25	1700	30	2.0mmV2	2.0mm 750	高耐温、高模量, 电视后壳 High temperature resistance, high modulus TV back cover
	FR-2030L	9	0.94	25	1350	80	1.5mmV2	2.0mm 750	耐析出、耐候性,插线板外壳 Precipitation resistance, weather resistance, plug board cover

产品类别 Product Category	牌号 Grade	测试标准、测试项目 Test criteria, test items								特性及用途 Property and Application
		熔指 MFI g/10min (230°C, 2.16kg)	密度 Density g/cm³	拉伸强度 Tensile Strength MPa	弯曲模量 Flexural modulus Mpa	悬臂梁缺口冲击强度 Notched Izod impact strength J/m		阻燃性 Flame retardance	耐热球压 Heat resistant ball pressure °C	
		ASTM D1238	ASTM D792	ASTM D638	ASTM D790		ASTM D256	UL 94	IEC 60695	
无卤阻燃 PP Halogen-free flame retardant PP	NH-2027	9	1.05	20	1650	32		1.5mm-V0	125°C	电脑板盒,微波炉组件 Computer board box, microwave oven kit
	NH-2027A	5.5	1.05	18	1500	50		1.5mm-V0	75°C	高冲击, 电脑板盒、微波炉组件 High impact, computer board box, microwave components
	NH-2027H	4	1.14	19	1950	29		2.0mm-5VA	125°C	耐热、高GWIT, 微波炉组件 Heat resistant, high GWIT, microwave components
	NH-2027HG	16	1.12	17.5	1800	28		3.0mm-5VA	125°C	高流动、阻燃大制件产品 High flow, flame retardant large parts products
	NH-2027G	10	1.12	20	2100	26		1.5mm-V0	125°C	高刚、高断裂伸长率 High stiffness, high elongation at break