

产品类别 Product Category	牌号Grade	测试标准、测试项目 Test criteria, test items							特性及用途 Property and application
		熔指 MFI g/10min	洛氏硬 度 Rockw ell hardne ss	断裂伸 长率 Elonga tion at break %	弯曲强 度 Flexu ral Strengt h Mpa	弯曲模量 Flexural modulu s Mpa	悬臂梁缺 口冲击强 度 Notched Izod impact strength J/m	阻燃性 Flame retardance	
		ASTM D1238	ASTM D785	ASTM D638	ASTM D790		ASTM D256	UL 94	
玻纤增强 PPS Glass- fibre reinforced PPS	RF- 601G30	25, 300°C, 2.16kg	115	5	220	9200	90	1.0mmV0	玻纤增强, 电子连接器 Glass fiber reinforcement, electronic connectors
	RF- 601G40	20, 300°C, 2.16kg	115	3	220	12000	80	1.0mmV0	玻纤增强, 小家电配件 Glass fiber reinforcement, Small appliance accessories
	RF- 601G50	16, 300°C, 2.16kg	115	3	230	15000	80	1.0mmV0	玻纤增强, 节温器外壳 Glass fiber reinforcement, small household appliances accessories
玻矿增强 PPS Mineral- fibre reinforced PPS	RF- 601GMX	22, 300°C, 2.16kg	115	3	185	13000	55	1.0mmV0	玻矿增强, 电子调节器 Glass fiber mine reinforcement, electronic regulator
	RF- 601GM65 B	-	-	5	240	15000	100	1.0mmV0	玻矿增强增韧, 高频头 Glass fiber reinforced toughened, tuner